



SONOPHONE

PREMIXED PLASTER COMPOSED OF GYPSUM AND CELLULOSE FOR THE ACOUSTIC CORRECTION

SONOPHONE

Premixed plaster composed of gypsum and cellulose for the acoustic correction

<p>DESCRIPTION</p>	<p>Sonophone is a sound absorbing plaster to spray on internal surfaces. It makes the surface white and pleasing. It only requires the addition of water on site to create a mixture to pump and apply with the machine. It is perfect for new buildings and the refurbishment or renovation of the existing ones. It can be applied on plaster board sheets, on cement and steel surfaces. It is mainly used for convention centers, schools, canteens, religious buildings and places where it's necessary to correct the internal acoustic reverberation.</p>
<p>CHARACTERISTICS AND ADVANTAGES</p>	<p>Sonophone has excellent characteristics of fire reactivity and combustion, an aesthetically pleasing surface and it is without solution of continuity. Sonophone belongs to A1 fire reactivity class [UNI EN 13501-1], so it is incombustible. Sonophone has reached a score of flame and smoke spread of 0 [test conforming to ASTM E 84]. The index of light reflectance is excellent, it reached 86 if it is smoothed and 83 with the finishing by spraying application [test conforming to ASTM C 523]. It has excellent sound absorbing characteristics too. It was tested conforming to ASTM C 423 and E 795 and it has already a NRC of 0,75 with 25 mm of product, fully bonded to the structure. Sonophone requires only the addition of water and the use of mixing machines and traditional equipment for the mechanic application of lightweight plasters. It can be applied in layers from 13 mm of thickness. Its application is fast and efficient.</p>
<p>SURFACE PREPARATON</p>	<p>Before the application of Sonophone it is necessary to check that the surface is suitable for it. The surface must be clean, dry and free from soluble matter in water, oil and other contaminants. It must also be sufficiently solid and adherent to the substrate and able to carry the weight of the moistened Sonophone.</p> <p>Gypsum plasterboards: partition walls and ceilings built with gypsum plasterboards must be carefully treated with a suitable waterproofing primer before the application of Sonophone (Sinprimer W of Zetagi or something). This must be done using a sealing product for plasterboard. Lay a layer of binder, approved by Edilteco, on the whole surface before to apply Sonophone. It's recommended not to make a Sonophone layer greater than 25 mm.</p> <p>Concrete surfaces: the new concrete must mature at least 60 days before to apply Sonophone. Growth and remaining parts must be removed in order to get a smooth surface. Dust and other extraneous matters must be removed before the application of Sonophone.</p> <p>Galvanized steel surfaces: remove the possible dirt or oils on the galvanized steel surface.</p> <p>All steel (non galvanized) surfaces: remove the dust, mill scales, dirt and oils on the surface. All steel not galvanized surfaces must be painted with a suitable anti-rust paint.</p>
<p>MIXING</p>	<p>Sonophone can be mixed within the mixer of a traditional or continuous plastering machine, suitable to apply cement-based lightweight plasters. The mixer must be clean and free of previous mixed matter. The mixing time and the number of turns must be adjusted in order to give the right texture to the mix, with a density of the wet product of 610-720 kg/m³. With a traditional mixer use a means of measuring to measure the right mixing water quantity and add the water. Use approximately from 20,5 to 24,5 L each bag of Sonophone. The mixing must carry on until the material is completely wet and the mixture without grains and with a pasty texture.</p>



dBred Noise Reduction Division



Edilteco S.p.A. Via dell'Industria, 710 - 41038 San Felice sul Panaro (MO) Italy
Ph. +39 0535 82161 - Fax +39 0535 82970 - www.edilteco.com | info@edilteco.com



COMPANY WITH
QUALITY SYSTEM
CERTIFIED BY DNV GL
= ISO 9001 =

APPLICATION	The application of a thickness of Sonophone can be done following this order: 1) For thickness up to 13 mm: only one layer. 2) For thickness equals or greater than 14 mm: apply other layers after the dry of the previous ones. Sonophone must not be used if it contains partially frozen or encrusted material. Sonophone can be applied spraying standard plasters or in continuum with a wide range of pumping. The dimensions of the nozzle's hole and the air pressure must be regulated to get the desired surface finishing. On Sonophone White it is possible to use mineral-based painting (ECAP STP or similar) only with spray method.
TEMPERATURE AND VENTILATION	<ul style="list-style-type: none"> The minimal air and substrate temperature for the application is 4 °C, which must be maintained during the Sonophone application and the next 24 hours. It's necessary to guarantee the ventilation in order to correctly dry the plaster after the application. It's recommended not to create closed areas that prevent air circulation and ventilation. The right hour air circulation is 4 times the air volume in the room.
DELIVERY AND STORAGE	Sonophone must be stored dry until its usage. The material's pallets must be kept high from the ground, under a roofing and far from moist surfaces. All the material exposed to water must be eliminated. The stored material must be used before the expiry date.
SAFETY	After the use of Sonophone the surfaces are slippery. The contractor and the applicator will be responsible to signal the slippery surfaces. The signals must be in all areas where there is moist material. All the working areas must use the non-slip protective systems. The Safety Sheet of Sonophone is available on demand to sds@edilteco.it

All the indications provided in this technical data sheet are purely approximate and not binding for legal purposes. The data listed has been gathered from laboratory tests and it hence follows that in practical applications on buildings sites the final characteristics of the products may be subject to substantial variations depending on the meteorological conditions and the installations. The user must always check suitability of the product for its specific use, undertaking all liability implicit in and deriving from use of the product, as well as comply with all the methods and instructions for use generally referable to "workmanlike" execution. Edilteco S.p.A. reserves the right to change the contents of this technical data sheets on its final judgements. The spreading of this data sheet through any media, supersedes and cancels the validity of any other technical data sheet previously published.

SOUND ABSORBING FEATURES

		COEFFICIENT OF SOUND ABSORBING ASTM C 423 - UNI EN ISO 11654																	INDEX	ABSORBING CLASS		
		FREQUENCY (HZ)																				
APPLICATION		100	125	160	200	250	315	400	500	630	800	1000	1250	1600	2000	2500	3150	4000	5000			
1	Thick. 13 mm adherence	α_s	0,07	0,02	0,02	0,02	0,1	0,19	0,23	0,28	0,41	0,6	0,7	0,84	0,91	0,94	0,91	0,86	0,88	0,89	NRC = 0,50	-
		α_p	0,05		0,10		0,30		0,70		0,90		0,90		0,90		0,90		0,90		$\alpha_w = 0,35$ (MH)	D
2	Thick. 25 mm adherence	α_s	0,06	0,04	0,14	0,15	0,3	0,44	0,6	0,8	0,91	1,05	1	0,93	0,91	0,88	0,9	0,92	0,93	0,99	NRC = 0,75	-
		α_p	0,10		0,30		0,80		1,00		0,90		0,95		0,95		0,95		0,95		$\alpha_w = 0,60$ (MH)	C
3	Thick. 13 mm semi-adherence	α_s	0,17	0,19	0,29	0,35	0,56	0,61	0,63	0,68	0,7	0,72	0,72	0,78	0,77	0,79	0,82	0,86	0,89	0,92	NRC = 0,70	-
		α_p	0,20		0,50		0,65		0,75		0,80		0,90		0,90		0,90		0,90		$\alpha_w = 0,70$ (H)	C
4	Thick. 50 mm semi-adherence	α_s	0,24	0,3	0,38	0,49	0,64	0,84	0,85	0,85	0,82	0,79	0,81	0,86	0,82	0,86	0,86	0,86	0,92	0,95	NRC = 0,80	-
		α_p	0,30		0,65		0,85		0,80		0,85		0,90		0,90		0,90		0,90		$\alpha_w = 0,85$	B
5	Thick. 25 mm semi-adherence	α_s	0,25	0,28	0,37	0,52	0,74	0,73	0,73	0,8	0,8	0,82	0,82	0,87	0,93	0,91	0,91	0,93	0,94	0,99	NRC = 0,80	-
		α_p	0,30		0,65		0,80		0,85		0,90		0,95		0,95		0,95		0,95		$\alpha_w = 0,85$ (H)	B
6	Thick. 25 mm cavity wall	α_s	0,96	0,44	0,42	0,46	0,53	0,48	0,5	0,64	0,71	0,82	0,88	0,94	0,97	0,96	0,98	1,01	0,98	1,08	NRC = 0,75	-
		α_p	0,60		0,50		0,60		0,90		0,95		1,00		1,00		1,00		1,00		$\alpha_w = 0,7$ (H)	C



dBred Noise Reduction Division



Edilteco S.p.A. Via dell'Industria, 710 - 41038 San Felice sul Panaro (MO) Italy
Ph. +39 0535 82161. Fax +39 0535 82970. www.edilteco.com | info@edilteco.com



COMPANY WITH
QUALITY SYSTEM
CERTIFIED BY DNV GL
= ISO 9001 =

CHARACTERISTIC	VALUE	NORM
Colour:	white, black	-
Packaged in:	bags of 20,5 kg	-
Dry density:	368 kg/m ³	ASTM E605
Wind erosion:	0,003 g/m ²	ASTM E859
Adherence resistance:	1173 kg/m ²	ASTM E736
Compressive resistance:	0,17 Mpa	ASTM E761
Fire reactivity:	A1	UNI EN 13501-1
Consumption:	4 - 4,5 kg each cm of thickness according to the surface irregularity	-



dBred Noise Reduction Division

DS SONOPHONE . Rev 07/2017 . GB



Edilteco S.p.A. Via dell'Industria, 710 . 41038 San Felice sul Panaro (MO) Italy
Ph. +39 0535 82161 . Fax +39 0535 82970 . www.edilteco.com | info@edilteco.com



COMPANY WITH
QUALITY SYSTEM
CERTIFIED BY DNV GL
= ISO 9001 =