




DRYSTOP H

WATERPROOF LIQUID FOR THE CREATION OF A BARRIER AGAINST THE RISING DAMP

DRYSTOP H

Waterproof liquid for the creation of a barrier against the rising damp

PRODUCT	Waterproof resinous liquid, specific for the creation of barriers against the capillary rising damp.	
PACKAGING AND STORAGE	<ul style="list-style-type: none"> · Bucket of 20 kg · Pallet: 27 buckets · It is recommended the use within 6 months. Store the product in a dry and fresh place, protected from frost or heat. 	
FIELDS OF APPLICATION	Renovation of masonry affected by rising damp.	
ADVANTAGES	Drystop H creates a continuous barrier against the rising damp, creating a chemical binding with the original material of the masonry.	
YIELD	From 300 to 800 gr of diluted product per linear meter, per cm of masonry's thickness, according to the type of masonry and its conservation.	
APPLICATION	<ol style="list-style-type: none"> 1. Realize a containing seal on both sides of the masonry, which must be previously made rough with a mixed mortar. 2. Drill as follows: <div style="display: flex; align-items: center; margin-top: 10px;">  <div style="margin-left: 20px;"> <p>S = thickness of the wall h = drilling height S - 7 cm = brick or mortar, not drilled, used as cap a = sloping angle, inversely proportional to the thickness's thickness, between 0° and 45°</p> <p>axe spacing of holes: 12 - 14 cm/m on one or more lines</p> </div> </div> 3. Prepare the solution pouring 0,6 kg of product into a bucket containing 19,4 kg of clean water. Mix quickly for approx. 8 minutes up to obtain a limpid solution. 4. Apply the solution by low-pressure injection within and not over 6 hours from the preparation. 	
WARNINGS	<ul style="list-style-type: none"> · Use with temperatures between +5 °C and +35 °C. · It suffers the frost. · Dilute with clean water. · Wear protective gloves. Avoid the contact with skin and eyes. · For further information about the renovation / dehumidification cycle, contact <i>Edilteco Technical Department</i>. 	
TECHNICAL CHARACTERISTICS	Fireproof odourless liquid.	
	Physical aspect / active:	blue emulsion / acid solution
	Specific weight:	0,9395 kg/L

All the indications provided in this technical data sheet are purely approximate and not binding for legal purpose. The data listed has been gathered from laboratory tests and it hence follows that in practical applications on building sites the final characteristics of the products may be subject to substantial variations depending on the meteorological conditions and the installation. The user must always check suitability of the product for its specific use, undertaking all liability implicit in and deriving from use of the product, as well as comply with all methods and instructions for use generally referable to "workmanlike" execution. Edilteco S.p.A. reserves the right to change the contents of this mechanical data sheet on its final judgements. The spreading of this data sheet through any media, supersedes and cancels the validity of any other technical data sheet previously published.



Thermal Insulation & Chemicals Division

DS DRYSTOP H . Rev 10/2018 . GB



Edilteco S.p.A. Via dell'Industria, 710 . 41038 San Felice sul Panaro (MO) Italy
 Ph. +39 0535 82161 . Fax +39 0535 82970 . www.edilteco.com | info@edilteco.com

© Copyright EDILTECO S.p.A. - Non authorized reproduction is forbidden.

COMPANY WITH
 QUALITY SYSTEM
 CERTIFIED BY DNV GL
 = ISO 9001 =