## EDIL-THERM® GT 100

## EPS THERMAL INSULATING BOARD WITH GRAPHITE

EDIL-THERM® GT 100 EPS thermal insulating board with graphite								
PRODUCT	EPS board, class 100, with graphite. Content of recycled material/byproduct (post-consumer) ≥ 10% *							
PACKAGING AND STORAGE	Board with straight edge 500 x 1000 mm (0,50 m²). • Thicknesses: from 30 to 180 mm. • Packaging: pallets prepared with stretch wrap. • Store in a cool and dry place, away from frost and water.							
APPLICATION FIELDS	<ul> <li>External wall thermal insulation (EWI).</li> <li>Internal thermal insulation for walls and ceilings.</li> <li>Thermal insulation of prefab building.</li> <li>Refurbishment and renovation of façades.</li> <li>Elimination of construction and general thermal bridges.</li> </ul>							
APPLICATION	See the "Edil-Therm® Catalogue" or contact the Edilteco Technical Department.							
WARNINGS	<ul> <li>Do not apply under the direct sunlight or with temperatures higher than +35 °C. If the gluing and the smoothing mortar is made under the direct sunlight, take the necessary precautions (e.g. the meshes covering the scaffolding or other).</li> <li>Do not apply under the rain, at temperatures lower than +5 °C or with risk of frost.</li> <li>Apply with relative humidity between 45% and 80%. Do not apply with relative humidity too low.</li> <li>For the detailed methods of use and application consult the <i>"Edil-Therm® Catalogue"</i>, or contact the Edilteco Technical Department.</li> </ul>							
TECHNICAL CHARACTERISTICS	DESCRIPTION	CODIFICATION Uni en 13163	UNIT OF MEASURE	VALUE	STANDARD			
	Length:	L2	mm	± 2	EN 822			
	Width:	W2	mm	± 2	EN 822			
	Thickness:	T2	mm	± 2	EN 823			
	Orthogonality:	S2	mm/mm	± 2/1000	EN 824			
	Planarity:	P4	mm	± 4	EN 825			
	Dimensional stability:	DS(N)	%	± 0,2	EN 1603			
	Compressive stress:	CS(10)	kPa	≥ 100	EN 826			
	Flexural strength:	BS	kPa	≥ 200	EN 12089			
	Declared thermal conductivity +10 °C:	$\lambda_{_{D}}$	W/(mK)	0,031	EN 12667			
	Limit temperature of use:	-	°C	75÷80	-			

\* % by weight of EPS



Thermal Insulation & Chemicals Division



Edilteco S.p.A. Via dell'Industria, 710 . 41038 San Felice sul Panaro (M0) Italy Ph. +39 0535 82161 . Fax +39 0535 82970 . www.edilteco.com l info@edilteco.com

	DESCRIPTION	CODIFICATION Uni en 13163	UNIT OF MEASURE	VALUE	STANDARD		
TECHNICAL CHARACTERISTICS	Fire reactivity:	-	Class	E	EN 13501-1		
	Factor of resistance to water vapour:	MU	μ	30 ÷ 70	EN 12086		
	Volume (± 10%):	р	kg/m³	16/18	EN 1602		
	Water absorption by total immersion for a long period:	WL(T)	%	≤ 3	EN 12087		
	Specific thermal capacity:	-	J/[kg.K]	1450	UNI EN 12524		
DECLARED THERMAL CONDUCTIVITY	THICKNESS	VALUE - R <sub>0</sub> =(m²K)/W		STAN	STANDARD		
	30 mm	1,00					
	40 mm	1,30					
	50 mm	1,65			EN 12667		
	60 mm	2,00					
	70 mm	2,30					
	80 mm	2,65					
	90 mm	3,00		EN 1			
	100 mm	3,30					
	120 mm	4,00					
	140 mm	4,65					
	150 mm	4,98					
	160 mm	5,30					
	180 mm	6,00					

All the indications provided in this technical data sheet are purely approximate and not binding for legal purpose. The data listed has been gathered from laboratory tests and it hence follows that in practical applications on building sites the final characteristics of the products may be subject to substantial variations depending on the meteorological conditions and the installation. The user must always check suitability of the product for its specific use, undertaking all liability implicit in and deriving from use of the product, as well as comply with all methods and instructions for use generally referable to "workmanlike" execution. Editeco S.p.A. reserves the right to change the contents of this mechanical data sheet on its final judgements. The spreading of this data sheet through any media, supersedes and cancels the validity of any other technical data sheet previously published.



Thermal Insulation & Chemicals Division



Edilteco S.p.A. Via dell'Industria, 710 . 41038 San Felice sul Panaro (MO) Italy Ph. +39 0535 82161 . Fax +39 0535 82970 . www.edilteco.com l info@edilteco.com

DS EDIL-THERM® GT 100 . Rev 09/2021 . GB

