



# GUM GUM Spray

IMPACT SOUND INSULATION LAYER  
COMPOSED OF PREMIXED RUBBER GRANULES

## GUM GUM Spray Impact sound insulation layer composed of premixed rubber granules

COMPOSITION	Impact sound insulation layer to be realized directly on site, composed of premixed SBR rubber granules ("A" Part), with controlled grain size and unique selected pre-batched binders, in bucket, to be mixed with a second liquid additive ("B" Part), for a manual or mechanical application.
PACKAGING AND STORAGE	<ul style="list-style-type: none"> <li>· Bucket of 13 kg: 8 kg of premixed SBR rubber ("A" Part) + 5 L of liquid additive ("B" Part).</li> <li>· Store in a dry and fresh place, away from frost and water. Use within 6 months.</li> </ul>
CONSUMPTION	3 kg/m <sup>2</sup> per 6 mm thickness - 5 kg/m <sup>2</sup> per 10 mm thickness.
FIELDS OF APPLICATION	<ul style="list-style-type: none"> <li>· Resilient layer for the reduction of impact noises in systems made of floating screeds, particularly suitable in the realization of floating screeds with a low thickness, also in case of installation without levelling layer.</li> <li>· Reduction of impact noises on stairs.</li> <li>· Soundproof layer to be applied in spaces between walls of double brick partition walls on clay-cement mix walls.</li> <li>· Realization of separating under-wall layers or covering of acoustic bridges, such as pillars and concrete beams.</li> <li>· Acoustic insulating treatment of inner courts for the passage of installations, individual discharge pipes made in PVC or similar.</li> </ul>
SURFACE PREPARATION	The surface must be clean, sufficiently solid, free from detached parts, dust and residual insulating materials.
APPLICATION	<p>For detailed indications please contact <i>Edilteco Technical Department</i>.</p> <p><b>Manual application:</b> drill (or cement mixer or horizontal mixer).</p> <ol style="list-style-type: none"> <li>1. Pour the liquid additive ("B" Part) into the bucket.</li> <li>2. Mix for at least 2 minutes to obtain an adequate mixture. Start the application phase using a smoothing metal trowel.</li> </ol> <p><b>Manual application time:</b> approx. 30 minutes at +20 °C and 70% humidity.  <b>N.B:</b> the mixed product can remain in the container up to 30 minutes at +20 °C and 70% humidity. It is possible to add 1/2 litre of clean water per bucket, mixing the product for 1 minute until obtaining an adequate mixing.</p> <p><b>Application with plastering machine (type Gum Gum Machine) equipped with mixing tank:</b></p> <ol style="list-style-type: none"> <li>1. Pour "A" Part and "B" Part into the hopper (it can contain and mix 3 buckets of Gum Gum Spray at the same time).</li> <li>2. Mix for at least 2 minutes to obtain an adequate mixture, then, pour the mixture in the hopper below.</li> <li>3. Moisten the material-holder pipe and start spraying (operation to be done only before the first mixing).</li> <li>4. It is possible to use a material-holder pipe smaller than 25 m.</li> <li>5. Gun nozzle Ø 14 mm.</li> </ol>



dBred Noise Reduction Division



Edilteco S.p.A. Via dell'Industria, 710 . 41038 San Felice sul Panaro (MO) Italy  
Ph. +39 0535 82161 . Fax +39 0535 82970 . [www.edilteco.com](http://www.edilteco.com) | [info@edilteco.com](mailto:info@edilteco.com)

© Copyright EDILTECO S.p.A. - Non authorized reproduction is forbidden.

COMPANY WITH  
QUALITY SYSTEM  
CERTIFIED BY DNV GL  
= ISO 9001 =

	CHARACTERISTIC	VALUE	NORM
TECHNICAL CHARACTERISTICS	Walkability:	approx. 24/36 hours for a 6 mm thick. (according to climate conditions and to the absorption of the surface anchorage)	-
	Percentage of recycled material:	89%	-
	Colour:	black	-
	Applicable thickness:	from 6 to 10 mm	-
	Thermal conductivity $\lambda_0$ :	0,074 W/mK	UNI EN 12667
	Dynamic stiffness $s'_d$ :	20 MN/m <sup>3</sup> (average value) *	UNI EN 29052-1
	Impact sound insulation $\Delta L'n$ (test on site):	25 dB	UNI EN ISO 16283-2
	Impact sound insulation $\Delta L_w$ :	18 dB	UNI EN ISO 10140-3
	Compressibility:	0,6 mm *	UNI EN 12431
	Environmental temperature for the application:	5 °C ÷ 30 °C	-
WARNINGS	<ul style="list-style-type: none"> <li>Do not apply under the direct sunlight or with temperature above +35 °C. If the application is made under the direct sunlight, necessary precautions must be taken (e.g. such as covering mesh for scaffolding).</li> <li>Do not apply under the rain, with a temperature below +5 °C or with frost risk. In any case, do not add anti-freezing products.</li> <li>Apply with relative humidity between 45% and 80%. Do not apply with a too low relative humidity.</li> <li>For the detailed methods of use and application contact <i>Edilteco Technical Department</i>.</li> </ul>		

All the indications provided in this technical sheet are purely approximate and not binding for legal purpose. The data listed has been gathered from laboratory test and it hence follows that in practical applications on building sites the final products may be subject to variations depending on meteorological conditions and the installation. The user must always check suitability of the product for its specific use, undertaking all liability implicit in and deriving from use of the product, as well as comply with all methods and instruction for use generally referable to "workmanlike" execution. Edilteco S.p.A. reserves the right to change the contents of this mechanical data sheet on its final judgment. The spreading of this data sheet through any media, supersedes and cancels the validity of any other technical data sheet previously published.

\* Value obtained on thickness 6 mm



dBred Noise Reduction Division

DS GUM GUM SPRAY . Rev 07/2021 . GB



Edilteco S.p.A. Via dell'Industria, 710 . 41038 San Felice sul Panaro (MO) Italy  
Ph. +39 0535 82161 . Fax +39 0535 82970 . [www.edilteco.com](http://www.edilteco.com) | [info@edilteco.com](mailto:info@edilteco.com)

COMPANY WITH  
QUALITY SYSTEM  
CERTIFIED BY DNV GL  
= ISO 9001 =

© Copyright EDILTECO S.p.A. - Non authorized reproduction is forbidden.